

---

No. 26 Taishan Road  
Suzhou New District  
Suzhou Jiangsu  
P.R. China

---

Z TAIYO INK (SUZHOU) CO., LTD.

Tel: +86-512-6665-5550  
Fax: +86-512-6665-5057

Dual-component, alkaline developable

Liquid photo imageable solder mask

**PSR-4000 Z100 / CA-40 Z26K**

July. 2006

**1. FEATURE:**

PSR-4000 Z100 / CA-40 Z26K is a Photo imageable liquid solder mask ink (alkaline –developable type), designed for screen printing with wide process window, high photo speed and excellent resistance to gold plating ( electro / electroless ).

**2. SPECTIFICATIONS:**

Product name:	Main agent: PSR-4000 Z100
	Hardener: CA-40 Z26K
UL name:	Main agent: PR-4000 Z100
	Hardener: CA-40 Z26K
Color:	Main agent: Green
	Hardener: Milk white
Mixing ratio:	Main agent: Hardener = 70 30 (by wt.)
Viscosity after mixing:	150±15 dPa.s (Cone-plate viscometer 5min <sup>-1</sup> /25 )
Solid content:	75 wt%
Specific Gravity:	1.3 (After mixing)
Tack dry window:	80 ×60 min (Max)
Exposure:	350-550 mJ/cm <sup>2</sup> (Under Mylar film)
	250-390 mJ/cm <sup>2</sup> (On solder mask)
Post cure:	150 ×60min
Pot life:	24 Hrs. (stored at dark & lustration place and closed, 25 or below)
Shelf life:	180 days after production (stored at dark place, 20 or below)

**3. PROCESS CONDITIONS:**

Process	Condition	Tolerance window
Test panels:	FR-4 (thickness 1.6mm)	-
Pretreatment:	Acid rinse → Buff scrubbing → Water rinse → Dry	-
Print:	100mesh	[100-125mesh]
Hold time	10 min	[10-20 min]
Pre-cure:	A: double side printing using pin and double side exposure or single side exposure	[80 60min] ( Max )
	80 20-30min (Hot air convection oven)	
	B: two times printing and pre-cure for double side exposure	
	1 <sup>st</sup> : 80 10-15 min (Hot air convection oven)	
	2 <sup>nd</sup> : 80 20-25 min (Hot air convection oven)	
Exposure:	350 mJ/cm <sup>2</sup> (Under Mylar film)	[350-550 mJ/cm <sup>2</sup> ]
	250 mJ/cm <sup>2</sup> (On solder mask)	[250-390 mJ/cm <sup>2</sup> ]
	Halogen lamp 7kW (ORC HMW-680GW)	
Hold time:	10 min	[10-20 min]
Development:	Solution: 1wt% Na <sub>2</sub> CO <sub>3</sub>	
	Temp. 30	
	Spray pressure 0.196Mpa	[0.196-0.245Mpa]
	Time: 60s	[60-90s]
Water rinse:	Temp. 25	[20-30 ]
	Spray pressure 0.1Mpa	[0.1-0.15Mpa]
	Time: 60s	[45-60s]
Post cure:	150 60 min (Hot air convection oven)	[150 30-90 min]

**4. ATTENTION ON PROCESS:**

- a) As to operation environment, it is necessary to control temperature, humidity and dust. Please use the yellow lamp, or Ultraviolet ray filter , do not use the white lamp or sunlight.
- b) Incompetent mixing will cause quality problem, such as gloss uneven and post cure problem.
- c) The optimum coating thickness is 20 to 30  $\mu\text{m}$  (after curing); Thinner coating tends to lower the thermal and gold plating resistance. Thicker coating tends to longer drying time and impress when exposure.
- d) If the viscosity is too high to print, can use some solvent such as Diethylene Glycol Monoethyle Ether Acetate (Carbitol Acetate) or Reducer-J, the quantity of the solvent can not exceed 2%, (one Kg ink can add 20cc solvent at best), otherwise, it may cause teardrop or lower resistance to thermal and gold plating.
- e) As every plant's drying equipments, process condition and quality target is different, so the temperature and drying time may also have difference. Please do verification test to define the operating conditions.
- f) As every plant's exposure equipments, process condition and quality target is different, so the exposure energy and development time may also have difference. Please do verification test to define the operating conditions.
- g) Please adjust the development solution, temperature, spray pressure and time follow this data to decrease the undercut and get the excellent result.
- h) Insufficient cure of the ink can lower the thermal resistance, and excess cure can lower gold plating resistance. Furthermore, Curing condition of the solder mask ink should be defined together with the curing condition of the marking ink.
- i) Excessive cure of the ink will cause the copper oxidation on the lamination, which will discolor the ink. Please do verification test to define the temperature and time.

CA: Diethylene glycol monomethyl ether acetate (B.P 217 deg. C)

**5 . INK PROPERTIES:****5.1 TACK DRY WINDOWS:**

Drying time (80 °C)	50min	60min	70min	80min
Developability	OK	OK	OK	NG

**5.2 PHOTO SENSITIVITY:**

Item	Thickness	Energy		Result
	um	mJ/cm <sup>2</sup> (under Mylar)	mJ/cm <sup>2</sup> (on S/M)	
Sensitivity Kodak No.2	22±2	350	245	6step
		450	315	7step
		550	385	8step
Resolution Between QFP pads	40±2	350	245	50 um
		450	315	50 um
		550	385	50 um

(1 min development)

**6. PROPERTIES:**

<b>Item</b>	<b>Test Method</b>	<b>Result</b>
Adhesion	Taiyo internal method Cross hatch peeling	100 / 100
Pencil hardness	Taiyo internal method No scratch on copper	6 H
Thermal resistance	Rosin flux 260 /30sec , 1cycle	Passed
Acid resistance	10vol% H <sub>2</sub> SO <sub>4</sub> 20 /20min. (Dip) Tape peeling test	Passed
Alkaline resistance	10wt% NaOH 20 /20min. (Dip) Tape peeling test	Passed
Solvent resistance	PGM-Ac 20 /30min. (Dip) Tape peeling test	Passed
Insulation resistance	IPC comb type (B pattern) Humidification: 25-65 /90%RH/ DC100V Measurement: DC500V 1min.	Initial 1.8×10 <sup>13</sup> ohm Conditioned 5.5×10 <sup>11</sup> ohm
Dielectric constant	Taiyo internal method Values at 1MHz Humidification: 25-65 /90%RH/ DC100V	Initial 4.13 Conditioned 4.5
Dissipation factor	Taiyo internal method Values at 1MHz Humidification: 25-65 /90%RH/ DC100V	Initial 0.021 Conditioned 0.035
Electro gold plate	Internal lab test Ni 5um Au 1um	Passed
Electroless gold plate	Internal lab test Ni 3um Au 0.03um	Passed

Note:

- The above-mentioned data is based on TAIYO INK (SUZHOU) Company's laboratory test. As every plant's equipments, environment and parameters have difference, the data is only for your reference.
- Please work in accordance with MSDS.